

PatchGuard™ Ultra

Technical Datasheet



Description

PatchGuard Ultra is a discrete sacrificial anode applied to patch repairs on reinforced concrete structures which are corroding as a result of chloride ingress or concrete carbonation.


Many structures suffer corrosion damage due to the incipient effect following concrete patch repairs. Although the fresh mortar in patch repairs halts corrosion of the steel within, it does not deal with chloride contaminated concrete outside the patch repair which is the cause of the corrosion. This leads to further corrosion damage at the periphery of the repair.

PatchGuard Ultra anodes redress the electrochemical imbalance induced through removal of the corrosion process from steel in the patch. PatchGuard Ultra anodes corrode preferentially to the surrounding steel, protecting it from further corrosion damage.

PatchGuard Ultra anodes are located within the parent concrete. Protective current is thus delivered directly to the steel outside the patch which is at greatest corrosion risk as opposed to clean steel within the patch repair. In addition, there is no compromise in the quality of the concrete repair material that can be used in reinstatement, as is typically the case for sacrificial anodes placed within patch repairs. The insulating properties of bonding primers prevents their use with traditional patch anodes – however, as PatchGuard Ultra is placed in the parent concrete primers may be used which leads to an enhanced repair bond.

Features and Advantages

- Simple, single small volume unit
- Corrosion resistant attachment system
- Rapid installation—no additional break out
- Bonding primers can be used
- High resistivity repair mortars can be used
- Targeted application
- Pre-packaged application mortar
- Large charge capacity > 350kC*



Application

A location for the discrete anodes as close as practical to the edge of the broken out repair shall be selected and holes drilled into the parent concrete within the patch at locations identified by the engineer. A hole of dimensions 25 mm diameter by 120 mm long shall be drilled to house the PatchGuard Ultra anode unit.

Pre-wet the drilled hole with water for a minimum of 15 minutes. Once the excess water has been removed from the bottom of the hole, DuoCrete PG mortar shall be applied into the hole with a nozzle to ensure no entrapment of air voids within the mortar. The PatchGuard Ultra anode shall be placed into the hole and inserted such that the DuoCrete PG mortar surrounds the whole unit.

The protruding titanium wire from the anode shall be directly connected to the cleaned reinforcing steel within the patch repair by winding at least twice around the rebar and fixing the tail with the supplied cable tie.

Electrical continuity of the PatchGuard Ultra anode conductors and the reinforcing steel shall be confirmed. The patch repairs shall be immediately reinstated.

The PatchGuard Ultra anode installation can be monitored using half-cell potential surveys, current outputs and reinforcing steel corrosion rate measurements


Ancillary Material

The following ancillary materials are also available from CPT Ltd;

- DuoGuard1000/750/500/350/175 anodes for treatment of chloride contaminated concrete outside patch repairs
- Manganese dioxide reference electrodes
- Monitoring equipment to monitor steel corrosion activity

PatchGuard™ Ultra

Technical Datasheet



Product Data

Packaging :25 units per tub.

Storage :Tubs should only be opened when product is required.

The lid of the tub should be closed at all times when not in use. Do not remove silica gel!

Limitations

Concrete repair material cover to the PatchGuard Ultra unit must be a minimum of 20 mm. Concrete repairs must be undertaken in accordance with EN 1504. Any discontinuous steel should be electrically bonded to ensure continuity.

The time to achieve steel protection will be dependent on site conditions. Depolarisation of treated steel will be slower in moist conditions.

Specification Clause

The discrete anode shall be PatchGuard Ultra, a sacrificial alloy anode with an integral electrical connection which allows fixing of the anode at a range of distances from the reinforcing steel and which is formed of a material more noble than steel, the anode unit being embedded within a hole within the patch using a pliable viscous backfill mortar of pH <12.4.

Health and Safety

Protective clothing must be worn.

Wear gloves and eye protection at all times.

Design of the PatchGuard Ultra system should be undertaken by a competent design engineer.

For technical and sales support please contact us at;

Concrete Preservation Technologies Ltd,

Unit 1, Palmer Business Court

Manor House Road,

Long Eaton, Nottingham,

United Kingdom, NG10 1LR

t: +44 (0)115 9724 238

f: +44 (0)115 9220 316

www.cp-tech.co.uk



Cert No. 10159

ISO 9001